

www.deuchem.com



德謙企業股份有限公司 新竹縣湖口鄉新竹工業區光復北路92號 TEL:886-3-5984035 FAX:886-3-5983301

DEUCHEM CO., LTD. 92, Kuang-Fu North Road, Hsinchu Industrial Park, Hu-kou, Hsinchu, Taiwan TEL: 886-3-5984035 FAX: 886-3-5983301

Levaslip 873

Leveling Agent

DESCRIPTION

Levaslip 873 provides leveling, slip and substrate wetting for mat coatings. It is especially effective in orientation enhancement of silica.

TYPICAL PROPERTIES

These values are used as reference. For detail product specifications, please contact our distributor or sales department.

Composition	: modified polysiloxane
Appearance	: slight yellow slight hazy
	liquid
Non-volaitle content	: >95%
Specific gravity	: 1.04 - 1.05
Reflective index	: 1.430 - 1.450 (25°C)

FEATURES

- To improve orientation of silica in mat coatings, reduce uneven gloss and orange peel.
- It can be reduce coefficient of friction and improve scratch resistance.
- It is lower surface tension, improves substrate wetting.
- Good compatibility.
- If need to re-coat, please test recoatability.

APPLICATIONS

- N/C lacquer
- 2K PU coatings

DOSAGE & USE

- 0.1 0.5% based on total formulation. It is recommended to carry out serial test of Levaslip 873 at various levels to obtain optimun dosage.
- For easy to use, it's better to predilute Levaslip 873 with a suitable solvent.

PACKAGE

Net Weight: 25 kg

STORAGE

- Keep away from sources of ignition and heat.
- Keep container tightly closed in a dry and wellventilated place.
- Stored between 0°C and 40°C.
- Below 15°C the product would become solid.
 Warm to room temperature and mix well before use. The efficiency is not influenced.

SAFETY

- The product requires special care in handling.
- Avoid any eye and skin contact.
- For further information please check MSDS.

The data presented is the result of careful and extensive research. However, since the actual conditions under which the materials may be used are beyond our control, no warranty of any kind, expressed or implied, concerning the use of the products is made.